



At Stahl-Becker you can order tinplates in production batches as well as single plates. High quality in every quantity.

Material	Material Number	DIN Material Code
TS275	1.0375	T57

All statements without guarantee

Stahl-Becker GmbH
Ottostraße 9-11
63150 Heusenstamm
Germany

Phone: +49 (6104) 4059-60 www.stahlbecker.com
Fax: +49 (6104) 4059-70 info@stahlbecker.com



Material Standard	DIN EN 10202		
Dimension standard	DIN EN 10202		
Products	Sheets		
	Sheets 533 x 765 mm:		
	Thickness (mm)	Width (mm)	Length (mm)
	0,20	533	765
	0,32	533	765
	0,42	533	765
	Sheets 530 x 760 mm:		
Dimensions	Thickness (mm)	Width (mm)	Length (mm)
	0,52	530	760
	0,58	530	760
	0,70	530	760
	0,80	530	760
	1,00	530	760
Tensile strength (Rm)	340-395 N/mm ²		
Surface	BK (bright), LG (slightly coldrolled)		
Coating	electrolytically tinned, shining finish, E 14,0/14,0 (the thickness of the tin layer is 14,0 g per m ²)		

All statements without guarantee

Stahl-Becker GmbH
 Ottostraße 9-11
 63150 Heusenstamm
 Germany

Phone: +49 (6104) 4059-60 www.stahlbecker.com
 Fax: +49 (6104) 4059-70 info@stahlbecker.com

